



MINERA CEMA S.A.

INDUSTRIAL, COMERCIAL Y FINANCIERA

AGROCEM 2

(Cód. 20701 – Emisión 2 – 01/11/07)

Hydrated Aluminosilicate

Clay

TYPICAL PHYSICAL PROPERTIES

Aspect:	Grey Powder
DOP wetted color:	Grey
Dry powder whiteness:	34 %
Oil absorption:	26 %
Moisture:	1.00 %
Water soluble salts:	2.00 %
Mohs hardness:	3
Specific gravity:	2.60

TYPICAL CHEMICAL PROPERTIES


Loss on ignition:	14.00 %
CaO:	0.50 %
MgO:	7.00 %
SiO ₂ :	53.00 %
Fe ₂ O ₃ :	10.00 %
Al ₂ O ₃ :	23.00 %

APPLICATIONS

- Paints
- Plastics
- Rubber
- Agroproducts

SCREEN TESTS

Retained on ASTM #200 (75 µm):	1.00 %
Retained on ASTM #325 (45 µm):	6.00 %



These data are based on an average calculated from several lots. Natural mineral products are subject to normal variations. The company has the right to modify the information when necessary.